Environmental Health Engineering and Management Journal. 2025;12:1521
http://ehemj.com
doi 10.34172/EHEM.1521

Environmental Health Engineering and Management Journal

Review Article

Environmental Health Engineering and Management

Open Access Publish Free

Occurrence, ecotoxicological aspects, and removal of pharmaceutical contaminants Using MOF-Based composite materials: A review

Maryam Salimi[1*], Ali Esrafili[2], Ahmad Jonidi Jafari[3], Hamid Reza Sobhi[4], Leili Esrafili[5]

[1]Department of Environmental Health Engineering, School of Health, Jiroft University of Medical Sciences, Jiroft, Iran
[2]Department of Environmental Health Engineering, School of Public Health, Iran University of Medical Sciences, Tehran, Iran
[3]Air Pollution Research Center, Iran University of Medical Sciences, Tehran, Iran
[4]Department of Chemistry, Payame Noor University, Tehran, Iran
[5]iPRACS, Faculty of Applied Engineering, University of Antwerp, Groenenborgerlaan 171, 2020 Antwerpen, Belgium

Abstract

Background: Pharmaceutical contamination of water resources from industries and domestic discharges poses a major global challenge due to its harmful effects on ecosystems and human health. Metal–organic frameworks (MOFs), a newly developed class of versatile porous materials, show great potential for photocatalytic pharmaceuticals removal. This review explores the occurrence and ecotoxicological impacts of pharmaceutical and discusses recent advances in its photocatalytic removal using advanced MOF-based composites.

Methods: A comprehensive review of peer-reviewed literature published before March 2025 was conducted using renowned bibliographic databases, including Web of Science and Scopus. Electronic databases were thoroughly searched using Medical Subject Headings (MeSH). The search included terms such as water, wastewater, water pollutants, ecotoxicology, pharmaceutical preparations, water purification, catalysis, photolysis, and metal–organic frameworks, along with their related synonyms.

Result: Recent research highlights the potential of MOF-based composites as highly effective catalysts for the photocatalytic degradation of pharmaceutical contaminants. The efficacy of this process, however, hinges on several critical factors, including the amount of catalyst used, the initial concentration of the pollutants, and the pH level of the medium. Fine-tuning these parameters is vital to optimizing performance and ensuring consistent, reliable results.

Conclusion: By efficiently decomposing pharmaceutical compounds when exposed to light, MOF-based composite materials play a crucial role in reducing their concentration within aquatic environments. MOFs serve as optimal platforms for developing a wide range of nanomaterials derived from their structures. In conclusion, their versatility and unique properties make them indispensable for advancing innovation across various scientific and technological domains.

Keywords: Water pollutants, Ecotoxicology, Pharmaceutical, Metal organic frameworks

Citation: Salimi M, Esrafili A, Jonidi Jafari A, Sobhi HR, Esrafili L. Occurrence, ecotoxicological aspects, and removal of pharmaceutical contaminants using MOF-based composite materials: a review. Environmental Health Engineering and Management Journal. 2025;12:1521. doi: 10.34172/EHEM.1521.

Article History:
Received: 14 January 2025
Revised: 5 April 2025
Accepted: 7 April 2025
ePublished: 23 December 2025

***Correspondence to:**
Maryam Salimi,
Email: m_salimi97@yahoo.com

Introduction

Water contamination is a critical, pressing global challenge that has drawn significant attention from researchers worldwide. This has spurred extensive studies aimed at understanding the presence of pollutants, developing precise methods to measure their concentrations, and creating innovative techniques to efficiently eliminate these contaminants from diverse water systems (1–3). In this regard, the presence of pharmaceutical compounds, as a subclass of organic contaminants, in water bodies worldwide has become a significant concern (4). These compounds include hormones, antibiotics, and other compounds, all of which have the potential to cause severe health problems and environmental damage (5). For example, the release of hormones such as 17α-ethynylestradiol has been shown to have endocrine-disrupting effects, even at minute concentrations (6). In addition, antibiotics are widely used in human and animal healthcare, and can have both bactericidal and bacteriostatic effects on microbial populations (7). These can reduce microbial diversity and have detrimental effects on the ecological functioning of the environment (8). These chemicals are transported and released to the environment by a variety of sources, including manufacturing plants, wastewater treatment plants, hospitals, individual households, and more, resulting

© 2025 The Author(s). Published by Kerman University of Medical Sciences. This is an open-access article distributed under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/4.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

in degraded water quality (9). As a result, identifying the potential risks posed by pharmaceuticals in the environment is a global concern. Therefore, it is urgent to remove pharmaceutical compounds from water systems to decrease harm to people and lower environmental hazards.

Advanced oxidation processes (AOPs) are recognized as critical components of chemical purification techniques, with the potential to oxidize various pollutants (10,11) non-selectively. Photocatalysis, as one of the various AOPs, has attracted considerable scholarly attention for its proven ability to degrade a broad spectrum of organic compounds, coupled with its high efficiency and the potential to harness light energy as a renewable, free resource (12). Upon the absorption of light with energy equal to or exceeding the band gap energy, a semiconductor generates a hole (h^+) in the valence band (VB) and an electron (e^-) in the conduction band (CB). The generation of such charge carrier is imperative for initiating the photocatalytic reaction and significantly enhances photocatalytic performance (13). Throughout the pollutant degradation process, photo-induced charges may migrate to the semiconductor surface, enabling their participation in oxidation and reduction reactions (14).

Over the past two decades, metal–organic frameworks (MOFs) have attracted considerable attention in photocatalysis. This surge in attention can be attributed to their extensive surface area, meticulously organized porous structures, and the ability to tune their organic linkers and metal clusters, which collectively impart remarkable photophysical and chemical properties (15). These materials have spurred innovative applications across multiple domains, such as gas storage, separation, catalysis, and drug delivery (16). An interesting aspect is that MOFs can function as semiconductors and facilitate charge-carrier transport under specific conditions, especially when the organic linkers or metal clusters are photoactivated (17). MOFs offer several advantages over traditional semiconductors like TiO_2 and ZnO for the photodegradation of pharmaceuticals: MOFs often exhibit broader light-absorption spectra, including the visible range, whereas TiO_2 and ZnO primarily operate in the ultraviolet region (18). The extended absorption range leads to greater efficiency in capturing solar energy for photocatalytic purposes. Also, due to their porous nature and high surface area, MOFs provide more active sites for photocatalytic reactions. These result in improved pollutant adsorption and degradation rates compared to the typically lower surface area of TiO_2 and ZnO. To date, a range of different MOFs have been synthesized, including Materials Institute Lavoisier (MILs) (19), zeolitic imidazolate frameworks (ZIFs) (20), University of Oslo frameworks (UiOs) (21), Christian-Albrechts-University frameworks (CAU) (22), Dresden University of Technology frameworks (DUT) (23), porous coordination networks (PCNs) (24), Hong Kong University of Science and Technology frameworks (HKUST) (25), to name only a few. MOFs have been widely explored as potential materials for the photodegradation of pharmaceuticals due to their unique properties and capabilities (26,27). Using MOFs as photocatalysts reveals limitations similar to those of conventional photocatalysts (28). A significant concern is the insufficient absorption of visible light, which significantly reduces the effectiveness of MOFs in photocatalytic applications (29,30). Additionally, rapid carrier recombination poses another critical challenge, further diminishing the photocatalytic activity of these materials. Together, these factors highlight the need for advancements in MOF technology to enhance their photocatalytic performance. The use of conventional MOFs in photocatalysis is constrained by challenges that mirror those of traditional photocatalytic materials, including durability and light-harvesting capabilities. To address MOF drawbacks and improve performance, a variety of components, including metal oxides, metal sulfides, metal-free carbonaceous materials, noble metals, two-dimensional $Ti_3C_2T_x$ (MXene), perovskites, etc., were used. The aims of this study were as follows: (1) to conduct a review of the literature on the occurrence and ecotoxicological risk assessment of pharmaceuticals, (2) to provide current information on the application of MOF-based composite materials for the photodegradation of pharmaceuticals in aquatic media, and (3) to explore semiconductors derived from MOF materials to foster further improvements.

Materials and Methods

A comprehensive assessment of scholarly literature from peer-reviewed and indexed sources was conducted, focusing on publications published up to March 2025. This analysis relied heavily on reputable bibliographic databases, including Web of Science and Scopus. These online resources were thoroughly explored using Medical Subject Headings (MeSH). The search methodology incorporated terms such as water, wastewater, water pollutants, ecotoxicology, pharmaceutical, water purification, catalysis, photolysis, and metal–organic frameworks, along with related synonyms, to ensure an exhaustive review of relevant literature. The selection criteria specified that only literature published in English and featuring at least one keyword matching the core terms under review in their titles, abstracts or keywords were eligible for inclusion. Furthermore, the study considered only works that had undergone rigorous peer review and were published in peer-reviewed journals. literature published after March 2025, along with those written in languages other than English, were excluded to maintain relevance and consistency. This approach was designed to ensure a thorough and representative review of relevant studies. Subsequently, the data extracted from the selected literature were systematically categorized,

synthesized, and integrated into the results and discussion sections of this analysis. The compiled and organized data were subsequently integrated into this study, contributing to the results and discussion sections, and were visually depicted through figures and tables for clarity and impact.

Results

Presence and ecological risk assessment of pharmaceuticals in the aqueous environment

While pharmaceuticals can treat illnesses, improper disposal and release into water bodies can result in serious environmental hazards and health risks (31). These compounds fall into many classes, including analgesics and anti-inflammatories, antibiotics, β-blockers, blood lipid regulators, contrast media, cytostatics, hormones, and psychiatric drugs (32). The presence of pharmaceuticals in wastewater from pharmaceutical manufacturers, municipal wastewater treatment plants (WWTPs), hospitals, and livestock farms has been reported in almost all regions of the world. Based on the collected data, Table 1 shows the presence of pharmaceutical compounds in water/wastewater samples.

Definitions of the analytical instrument abbreviations used in this table are as follows:

- **UPLC/TQD-MS:** Ultra-high-performance liquid chromatography coupled with tandem quadrupole mass spectrometry.
- **UPLC-Q Exactive Orbitrap-HRMS (HESI):** Ultra-performance liquid chromatography coupled with a Q-Exactive Plus Orbitrap high-resolution mass spectrometer equipped with heated electrospray ionization (HESI).
- **LC-MS/MS:** Liquid chromatography coupled with tandem mass spectrometry.
- **HPLC-MS/MS:** High-performance liquid chromatography coupled with tandem mass spectrometry.

On the other hand, the presence of pharmaceutical compounds in the environment has been linked to significant ecological disturbances. Therefore, the Risk Quotient (RQ) methodology has been employed in numerous studies worldwide to assess the risks posed by pharmaceutical residues to aquatic organisms. The RQ methodology has been extensively applied in a range of aqueous environments, including wastewater, groundwater, lake water, drinking water and so on. When RQ is less than 1, the environmental risk from pharmaceuticals is minimal; however, when RQ is equal to/or greater than 1, adverse effects on organisms are expected (40). Table 2 shows the ecological risk assessment of pharmaceutical compounds in different regions of the world.

Photocatalytic degradation of Pharmaceuticals by MOFs

MOFs are a group of porous crystalline materials that consist of metal ions or clusters and organic linkers. Compared to traditional semiconductor photocatalysts, MOFs exhibit structural flexibility and unique physicochemical properties, making them particularly effective for degrading organic pollutants. Furthermore, one of the most impressive features of MOFs as photocatalysts is their large surface area and porosity. When MOFs are irradiated with illumination (UV/Vis/natural sunlight) with energy equal to or greater than the MOF bandgap, the photogenerated electrons transfer from the VB to the CB, resulting in the formation of h^+ in the VB (45–47).

Table 1. The occurrence of pharmaceutical compounds in water/wastewater samples.

Name	Sampling point	Country	Concentration (ng/L)	Analytical method	Ref.
Acetaminophen	River water	India	6.81–247	UPLC/TQD-MS	(33)
Acetaminophen	Surface water	Nigeria	1–12430	UPLC-Q Exactive Orbitrap-HRMS	(34)
Acetaminophen	Groundwater	Nigeria	<0.5–349	UPLC-Q Exactive Orbitrap-HRMS	(34)
Acetaminophen	River water	India	6.81–247	UPLC/TQD-MS	(33)
Carbamazepine	WWTP effluent	New Zealand	595–793	LC-MS/MS	(35)
Ciprofloxacin	River water	China	ND–415	HPLC-MS/MS	(36)
Ciprofloxacin	Lake water	Uganda	2.0–41.0	LC-MS/MS	(37)
Ciprofloxacin	River water	China	ND–185.14	HPLC-MS/MS	(38)
Ciprofloxacin	River water	China	ND–35.68	HPLC-MS/MS	(39)
Diclofenac	WWTP effluent	New Zealand	152–561	LC-MS/MS	(35)
Norfloxacin	River water	China	ND–26.74	HPLC-MS/MS	(39)
Sulfamethoxazole	WWTP effluent	New Zealand	160-398	LC-MS/MS	(35)
Tetracycline	River water	China	ND–227	HPLC-MS/MS	(36)
Tetracycline	River water	India	1.25–98.6	UPLC/TQD-MS	(33)
Tetracycline	Lake water	Uganda	2.7–70.0	LC-MS/MS	(37)
Tetracycline	River water	China	ND–28.65	HPLC-MS/MS	(38)

Photogenerated holes can directly decompose pollutants and react with water and/or hydroxyl ions to produce hydroxyl radicals, a strong oxidizing species (48,49). Also, the photogenerated electrons may react with oxygen to form superoxide radicals (50). These oxidizing species can react with organic pollutants, degrading them into non-toxic or less toxic products such as carbon dioxide and water (51). A study conducted by Gao et al reported the synthesis of a Zeolite Imidazole Framework-8 (ZIF-8) for the photocatalytic degradation of oxytetracycline under visible light (52). According to experimental data, 90% of oxytetracycline can be degraded by ZIF-8 after 180 min when exposed to visible light, and the degradation rate reaches 69% after the fourth cycle. In a study by Wang et al (53), zirconium butoxide was used as a precursor for metal clusters. It successfully synthesized a novel UiO-66-based photocatalyst with different functional groups on the organic ligand, including UiO-66, UiO-66-NH_2, and UiO-66-$(OH)_2$. The findings revealed that the key role of the functional group-modified UiO-66-based photocatalyst is for acetaminophen degradation under simulated solar irradiation. It was determined that UiO-66-NH_2 displayed the best performance, with acetaminophen removal > 90% after 360 min of irradiation, exceeding the corresponding values for UiO-66 and UiO-66-(OH_2). On the other hand, numerous studies have investigated MOF-based composite materials for their potential to generate oxidizing species, which have been used to degrade antibiotics such as $BaTi_{0.85}Zr_{0.15}O_3$/MOF-5 (54), BiOBr/MIL-101(Cr) (55), and Bi_2S_3/MIL-53(Fe) (56). Table 3

Table 2. Ecological risk assessment of pharmaceuticals in aquatic environments in different regions of the world.

Country	Environment analyzed	Highlight	Ref.
Bangladesh	River	The levels of sulfamethoxazole, erythromycin-H_2O and tylosin in rivers were medium in terms of ecological risk.	(41)
Malaysia	Drinking water	There was no potential health risk from pharmaceuticals exposure for either adults or children.	(42)
Portuguese	Seawaters	Diclofenac poses a potential risk to aquatic organisms.	(43)
China	River	Ofloxacin showed RQ values above 1, indicating potential risk to aquatic organisms.	(44)

Table 3. Recent studies on the photodegradation of pharmaceuticals by MOFs- semiconductor composites and related materials.

Photocatalyst	Target	Light Source	Conditions	Optimal degradation efficiency	Ref.
CeO_2/MIL101(Fe)	Tetracycline	300 W Xe lamp (λ > 420 nm)	Volume solution: 100 mL Dosage: 0.3 g/L C_0: 20 mg/L Time: 120 min	83.5%	(57)
SnO_2/MOF-199	Metronidazole	75 W Hg lamp ($\lambda \approx$ 365.4 nm)	Volume solution: 20 mL Dosage: 2 g/L, C0: 40 mg/L, Time: 240 min	≈ 81%	(58)
DUT-5/Bi_2MoO_6	Tetracycline	300 W XL ($\lambda \geq$ 420 nm)	Volume solution: 100 mL Dosage: 0.1 g/L C_0: 20 mg/L Time: 60 min	84.2%	(59)
Bi_2MoO_6/NH_2-UiO-66	Oxytetracycline	350 W XL	Volume solution: 40 mL Dosage: 0.5 g/L C_0: 10 mg/L Time: 150 min	93.7 %	(60)
Bi_2WO_6/ZIF-8	Tetracycline	300 W mercury lamp	Volume solution: 100 mL Dosage: 0.2 g/L C_0: 20 mg/L Time: 80 min	97.8%	(61)
MOF-808/AgI	Tetracycline Hydrochloride	300 W XL	Volume solution: 100 mL Dosage: 0.2 g/L C_0: 20 mg/L Time: 80 min	93.65%	(62)
MIL-125(Ti)/GO	Tetracycline	250 W Xe lamp(-)	Volume solution: 100 mL Dosage: 0.1 g/L C_0: 20 mg/L Time: 90 min	90.1%	(63)
g-C_3N_4/NH_2-MIL-88B(Fe)	Ofloxacin	300 W Xe lamp (λ > 420 nm)	Volume solution: 50 mL Dosage: 0.25 g/L C_0 (OFL): 10 mg/L Time: 150 min	96.5%	(64)
g-C_3N_4 @MIL-101(Fe)	Oxytetracycline Hydrochloride	300 W Xe lamp (λ > 420 nm)	Volume solution: 40 mL Dosage: 0.5 g/L C_0 10 mg/L Time: 300 min	87.68	(65)

lists MOF-based composite materials used to degrade pharmaceutical pollutants.

Discussion

Occurrence and ecological risk assessment of pharmaceuticals in the aqueous environment

The data in Table 1 highlights the widespread occurrence of pharmaceuticals in water bodies, raising concerns about their ecological and health impacts. In addition, the presence of pharmaceuticals in aquatic environments has been reported in other parts of the world. For example, in Tunisia, antibiotics such as cefalexin and spiramycin were reported at concentrations ranging from 7.5 to 370 ng/L in WWTP effluent (66). Also, Younes et al reported high levels of sulfamethoxazole (1.72 µg/L), ciprofloxacin (0.31 µg/L), and azithromycin (0.25 µg/L) in municipal WWTP effluent in Beni-Suef, Egypt (67). Al-Maadheed et al detected the highest concentrations of metronidazole (5.46 µg/L) and ciprofloxacin (1.99 µg/L(68). A study conducted in Kenya showed that hospital wastewater could contain concentrations of pharmaceutical antibiotics 3–10 times higher than those measured in surface water and WWTPs (69). The measured mean concentrations of sulfamonomethoxine, penicillin G, and doxycycline in cattle wastewater in Yunnan (China) were 150.49, 91.71, and 49.00 µg/L, respectively (70). Overall, due to the continuous release of pharmaceutical residues from untreated or insufficient wastewater treatment, they have been widely detected in receiving aquatic ecosystems, including surface waters, groundwater, and treated water.

So far, several investigations have focused on the risks associated with pharmaceutical residues in water bodies, as shown in Table 2. Apart from these, a study conducted by Paíga et al in Portugal identified the potential risks associated with the release of human pharmaceuticals into rivers as an increasingly critical environmental health issue (71). It was determined that the RQs in WWTP effluent were higher than those present in the river. A variety of pharmaceuticals have been shown to pose risks to non-target species, with RQ values exceeding 1. The pharmaceuticals of concern include sulfamethoxazole, clarithromycin, azithromycin, fluoxetine, acetaminophen, ibuprofen, and diclofenac. They found algae to be the most sensitive species.

Additionally, ibuprofen and diclofenac appeared to have a greater impact on fish species. An RQ level exceeding 1 was also observed in daphnids exposed to acetaminophen. According to a study by Lei et al (72), 15 antibiotics from five classes were monitored in the surface waters of the Haihe River sub-catchment in North China. The risk was assessed using the calculated RQ, and amoxicillin, anhydro erythromycin, ofloxacin, norfloxacin, and enrofloxacin were identified as having the potential to pose high ecotoxicological risks that could negatively impact the aquatic ecosystem.

The rising frequency of pharmaceuticals detected in the environment is a significant and escalating concern. These substances, once introduced into natural ecosystems, can pose serious risks not only to various forms of wildlife but also to human health. To tackle this escalating issue, innovative strategies are essential, with advanced degradation methods, such as photocatalysis, emerging as promising solutions for dismantling pharmaceutical contaminants. The focus on photocatalyst degradation has intensified, primarily due to the continuous release of pharmaceutical residues into the environment, which poses a significant challenge to ecological balance.

Photocatalytic degradation of Pharmaceuticals by MOFs

To date, several studies have applied MOF in photocatalytic reactions (see Table 3). In this regard, MOFs composites with metal oxide/metal sulfide, such as Cu_2O (73), CeO_2 (57), BiOBr (74), In_2S_3 (75), and MoS_2 (76), have been widely used as photocatalysts for the degradation of pharmaceutical compounds owing to their unique properties. Among them, MOF/TiO_2-based composites are among the most commonly employed photocatalysts for this purpose. For instance, He et al recently synthesized a novel magnetic composite, MIL-101(Fe)/TiO_2, as a modified photocatalyst and evaluated its potential for tetracycline elimination (77). According to experimental results, the composite exhibited excellent tetracycline removal efficiency (92.76% in 10 min) under solar irradiation. Furthermore, the composite could be easily separated from aqueous solution with a magnet. Therefore, it can be reused multiple times, making it cost-effective and environmental-friendly. In a similar study, He et al successfully synthesized MIL-100(Fe)/TiO_2 composites via growing MIL-100(Fe) crystals on TiO_2, using surface-coated FeOOH as a precursor and utilized them for the degradation of tetracycline under light irradiation (78). Among them, all MIL-100(Fe)/TiO_2 photocatalyst composites showed greater photocatalytic activity than pristine TiO_2. Thus, the enhanced photocatalytic activity of the composites is attributed to a decrease in the optical band gap relative to pristine TiO_2. Also, the Fe–O clusters in MIL-100(Fe) not only effectively separate charge carriers but also promote photocatalytic activity via the Fe^{3+}/Fe^{2+} redox cycle. He et al prepared a MIL-101(Fe)/TiO_2 composite via solvothermal synthesis. They tested a combination of persulfate activation and photocatalysis for the removal of tetracycline, a pollutant model, under visible-light illumination (79). It was demonstrated that combining MIL-101(Fe)/TiO_2 and persulfate, not only led to generate sulfate radicals by enhanced persulfate activity via the synergistic effect between MIL-101(Fe) and TiO_2, but also enhances the separation of photo-generated charge carriers, which enhances the photocatalytic performance, improves the activation effect of persulfate, and eventually

achieves the remarkably efficient degradation of the target pollutants. A work by Wu et al explored the formation of a novel TiO_2@UiO-66-NH_2 nanocomposite via in situ solvothermal methods and demonstrated its application for tetracycline elimination (80). Owing to its effective charge separation and improved photocatalytic performance, the resulting nanocomposite exhibits superior photocatalytic activity for tetracycline decomposition compared with the single material. Interestingly, the nanocomposite exhibits outstanding recyclability even after the fourth cycle. These results highlight its potential for valuable applications.

Furthermore, Nazari et al successfully synthesized WO_3/ZIF-67 via the sol-gel method (81). Experimental results showed that WO_3/ZIF-67 composites exhibited remarkable removal efficiency for oxytetracycline under visible-light irradiation. The photocatalytic efficiency of WO_3/ZIF-67 against oxytetracycline could reach 91.5% within 60 min. Besides, the photocatalytic mechanism of WO_3/ZIF-67 composites was explored and proposed, showing the vital roles of active species, including $\bullet O_2^-$, •OH, and h^+, in the degradation of oxytetracycline during the photocatalytic reaction. Additionally, the photocatalyst reaction is as follows:

$$WO_3/ZIF - 67 + hv \rightarrow e^- + h^+ \quad (1)$$

$$h^+ (WO_3) + H_2O \rightarrow \bullet OH + H^+ \quad (2)$$

$$e^- (ZIF - 67) + O_2 \rightarrow \bullet O_2^- \quad (3)$$

$$\text{Oxytetracycline} + \bullet O_2^- / \bullet OH / h^+ \rightarrow CO_2 + H_2O + \text{Harmless Products} \quad (4)$$

Recently, there has been an increase in the use of MOF/bismuth-based semiconductor composites for the degradation of pharmaceutical pollutants (82,83). For instance, Tang et al focused on the fabrication of a Bi_2O_3@UiO-66 heterojunction photocatalyst via a solvothermal route for tetracycline degradation. The improved visible-light absorption and enhanced charge separation were responsible for the increased photocatalytic activity of Bi_2O_3@UiO-66 (84). Zhang et al synthesized a BiOI@PCN-222 composite photocatalyst with a mesoporous nanostructure. They discussed its synergy in enhancing the separation efficiency of photogenerated electron–hole pairs, as well as its self-decontamination and photocatalytic tetracycline degradation under visible-light irradiation (85). Also, Wang et al used one-step hydrothermal methods to prepare novel flower-like MIL-100(Cr)/BiOCl heterojunction photocatalysts with varying MIL-100(Cr) mass (86). Accordingly, the formation of a heterostructure between MIL-100(Cr) and BiOCl played a crucial role in enhancing photocatalytic performance by enabling intense interfacial contact between the two components, thereby accelerating carrier migration. Besides, the composite photocatalysts also yielded a higher photo-current intensity and a smaller arc radius in the EIS Nyquist plot than pure MIL-100(Cr) and BiOCl. The photocatalytic performance of the MIL-100(Cr)/BiOCl composite was evaluated by the photodegradation of oxytetracycline under visible-light illumination. The optimized MIL-100(Cr)/BiOCl composite demonstrated significantly accelerated oxytetracycline degradation rate constant compared with pure MIL-100(Cr).

To date, several studies have confirmed that combining MOFs with bismuth molybdate to construct heterojunctions improves their photocatalytic activity (60,61,87). Su et al successfully designed a Bi_2MoO_6/UiO-66-NH_2 (BUN-x, where x denotes the amount of added UiO-66-NH_2) heterojunction Z-scheme photocatalyst (51). The photocatalytic performance was determined under visible-light irradiation. Meanwhile, the excessive incorporation of UiO-66-NH_2 did not improve Bi2MoO6's ability to degrade ofloxacin and ciprofloxacin. The highest photocatalytic degradation removal efficiencies of ofloxacin and ciprofloxacin were observed in BUN-100, 100.0% and 96.0%, respectively, within 90 min. Also, the BET specific surface area of the BUN-100 composites was higher than that of pure Bi_2MoO_6 and displayed a narrower band gap. Moreover, Wu et al successfully fabricated a series of MIL-100(Fe) photocatalysts decorated with $Bi_2Sn_2O_7$, denoted as BMx ($x = 1, 3, 5, 7$), and investigated their photocatalytic performance for ciprofloxacin degradation (88). They found that the photocatalytic activity followed the order of BM5 > BM3 > BM1 > BM7 > MIL-100(Fe) > $Bi_2Sn_2O_7$. Zhang et al reported an efficient $CuBi_2O_4$@UiO-66-NH_2 core–shell nanostructures (89). They achieved this by decorating thin-layered UiO-66-NH_2 on the surface of $CuBi_2O_4$ nanorods under solvothermal conditions. The formation of heterogeneous contacts between $CuBi_2O_4$ and UiO-66-NH_2 played a vital role in enhancing photocatalytic performance. It provides significant advantages, including fast charge-carrier transfer and efficient utilization of visible light. The optimized $CuBi_2O_4$@UiO-66-NH_2 composition ($CuBi_2O_4$@UiO-66-NH_2(0.2)) delivers the fastest tetracycline hydrochloride photo-degradation kinetics among the tested catalysts, with a rate constant of 0.0126 min^{-1}.

In recent years, research on integrating MOFs with metal sulfides (including monometallic, bimetallic, and polymetallic sulfides) as photocatalysts to eliminate organic (90–92). This is because of its attractive features, including its response to visible light (93). In view of this, Chaturvedi et al (94) reported a CdS/MIL-53(Fe) photocatalyst synthesized by a two-step ultrasonic-assisted solvothermal method. They examined its photocatalytic activity under visible-light illumination using ketorolac tromethamine as a model pollutant. The high degradation level they obtained was 80% in 330 min, which was

ascribed to the high charge separation, retarded electron–hole recombination, and better visible light response of the prepared CdS/MIL-53(Fe) photocatalyst. The process of photocatalytic degradation of the tested pollutants was shown as follows (Equations 5– 8):

$$\text{Cds/MIL - 53(Fe)} + \text{hv} \rightarrow \text{Cds}(h^+)\,\text{MIL - 53(Fe)}(e^-) \quad (5)$$

$$e^- \left(\text{MIL} - 53\left(\text{Fe}\right)\right) + O_2 \rightarrow \bullet O_2^- \quad (6)$$

$$h^+ \left(\text{MIL} - 53\left(\text{Fe}\right)\right) + H_2O \rightarrow \bullet OH + H^+ \quad (7)$$

$$\bullet OH + \text{Ketorolac tromethamine} \rightarrow \text{Smaller molecules} \quad (8)$$

In another work, He et al examined the photocatalytic degradation of tetracycline, a model substrate, using the In_2S_3/MIL-100(Fe) photocatalyst (91). Characterization was performed, and factors affecting photocatalyst performance, including photocatalyst loading, initial tetracycline concentration, and pH, were investigated. To assess the phase of the used photocatalyst, XRD was performed on the In_2S_3/MIL-100(Fe) photocatalyst after three cycles. They observed that the intensity of the characteristic peaks and the phase structure of the catalyst showed no noticeable change before and after the photocatalytic reaction, indicating no deviation from the fresh In_2S_3/MIL-100(Fe) composite. In addition to metallic sulfides, zinc indium sulfide ($ZnIn_2S_4$), a bimetallic sulfide, has been widely used to construct heterojunctions with MOFs to promote carrier separation. For example, a study by Zhang et al reported that $ZnIn_2S_4$/MOF-525 prepared via a one-step solvothermal method could be used for degrading tetracycline via photocatalytic experiments (95). Their structural attributes were identified using techniques such as XRD, FT-IR, SEM, and TEM. The research results showed that the composite's photocatalytic activity enhancement was much higher than that of the pure component. Furthermore, the composite's stability was examined through a five-run cycling test, and its photocatalytic degradation efficiency showed no noticeable changes after five reuse cycles.

Recently, metal-free carbonaceous materials, such as carbon nitride, graphene oxide (GO), and carbon nanotubes, have attracted significant interest in photocatalysis (96,97). Wu et al examined MOF-801/GO composites and reported that they possessed excellent photocatalytic adsorption activity for the degradation of tetracycline (98). In the photocatalytic degradation process, h^+plays a key role. Also, the reaction of $h^+$with H_2O led to $\bullet OH$ formation. In another research work by Mi et al UiO-66 (Ce)/GO composites were synthesized via an in-situ growth method (99). The highest photocatalytic degradation rate of sulfamethoxazole was achieved over GO@UiO-66(Ce)-5, exhibited a markedly improved reaction rate constant relative to pure UiO-66(Ce) and pristine GO.

It is important to note that, when using photocatalysis to degrade pharmaceutical compounds, various intermediates may form (100). For the identification of intermediate compounds during photocatalytic degradation, liquid chromatography-mass spectrometry (LC-MS) is commonly employed. It is worth noting that some intermediate compounds may exhibit more undesirable effects than the parent compound (101). Therefore, in studies of the photo-degradation of pharmaceutical contaminants, toxicity evaluation is considered as necessary step, for which MTT assay is widely applied (102). In this regard, we have designed MIL-125(Ti) mixed linker/g-C_3N_4 for the removal of cefixime (103). The composite suppresses the recombination of electrons and holes, resulting in high photocatalytic activity. In addition, the cytotoxicity of the treated water sample was evaluated using human peripheral blood lymphocytes, the MTT assay results indicated negligible cytotoxic effects. Also, Cao et al synthesized a g-C_3N_4/MIL-68(In)-NH_2 heterojunction composite using an in situ solvothermal method assisted by ultrasonication for the photocatalytic degradation of ibuprofen (104). Under visible-light irradiation for 120 min, the 10 wt% g-C_3N_4/MIL-68(In)-NH_2 composite achieved 93% ibuprofen degradation, compared with only 9% for pure g-C_3N_4 and 68% for MIL-68(In)-NH_2. The heterojunction formed between g-C_3N_4 (Eg = 2.70 eV) and MIL-68(In)-NH_2 (Eg = 2.81 eV) led to the restriction of the recombination rate of charge carriers, which enhanced the photodegradation of ibuprofen. This, in turn, led to the generation of h^+, $\bullet OH$ and $\bullet O_2^-$, which were the main active species that play a vital role in the degradation of ibuprofen molecules.

In recent years, the use of noble metals and materials containing them to enhance MOF photocatalytic activity has attracted special attention owing to their excellent photoelectrochemical properties (105–107). Muelas-Ramos et al prepared and characterized NH_2-MIL-125 loaded with Pd, Pt, and Ag and investigated its activation under solar irradiation for acetaminophen degradation (108). All synthesized samples were more active than the pure UiO-66-NH_2, with Pt/NH_2-MIL-125 showing a high acetaminophen removal efficiency and rapid kinetics, as reflected by its rate constant (k). Additionally, the effects of various inorganic ions, such as NO_3^-, NO_3^-, SO_4^{2-}, and HCO_3^-, on acetaminophen degradation by Pt/NH_2-MIL-125 have been evaluated. Among them, HCO_3^- tended to react with the $\bullet O_2^-$, which could reduce the photocatalytic activity. The Pt/NH_2-MIL-125 photocatalyst maintained its high photocatalytic activity and structural morphology after three reuses, as confirmed by SEM and XRD analysis. In contrast, the formation of reaction by-products may block some pores in the material. In another work, the Pd/UiO-66 photocatalyst was synthesized by Yang et

al for the removal of tetracycline from a water solution (109). Under simulated solar irradiation, the modified UiO-66 exhibited significantly greater photodegradation activity toward tetracycline than pure UiO-66. Nyquist plots results confirmed that Pd/UiO-66 is an effective photocatalyst material owing to the increased mobility of photogenerated carriers. Table 3 lists MOFs composed of noble metals and related materials used to degrade pharmaceuticals.

Recently, MOF-on-MOF materials have attracted broad attention due to their ability to enhance the combination of the intrinsic physical/chemical properties and performance of individual compartments (110). For example, Zhang et al synthesized NH_2-MIL-88B(Fe)@MIL-100(Fe) by internal expansion growth for photocatalytic removal of tetracycline (100). The best-performing 0.5-bi-MOFs sample achieved 99% pollutant degradation in 90 min. The study found that degradation efficiency is influenced by catalyst dose, the initial tetracycline concentration, and solution pH. The photocatalyst also demonstrated high stability in tetracycline degradation over five consecutive reaction cycles. In a research study conducted by Zhao et al, a novel MOF-on-MOF composite, PCN-134/PCN-222 (coded as P21-X, where X represents the ratio of PCN-222 to PCN-134), was obtained for the first time via an epitaxial growth strategy (111). As a result, the composition (P21-3) exhibited the highest nizatidine degradation efficiency, reaching 90.81% within 120 minutes under light irradiation. Moreover, the composite photocatalysts showed a decrease in nizatidine photodegradation in water samples, in the following order: distilled water > tap water > river water > sea water. The authors attributed the drop to turbidity. In addition, the synthesized composite shows good reusability over five consecutive runs. Gao et al designed a NH_2-MIL-125@MIL-88B heterostructure for efficient tetracycline removal by solvothermal epitaxial growth of MIL-88B crystals onto the NH_2-MIL-125 surface (112). Almost all NH_2-MIL-125@MIL-88B heterostructures exhibited higher removal rates than pure NH_2-MIL-125 or MIL-88B. The performance was due to the synergistic effect between NH_2-MIL-125 and MIL-88B, as well as the electron-transfer facility between them.

Transition-metal carbides and carbonitrides (MXene) are a new class of two-dimensional nanomaterials mapped by the general formula $M_{n+1}X_nT_x$ ($n = 1–3$), wherein M represents an early transition metal, X is either carbon or nitrogen, T represents surface termination groups (–O, –OH, and/or –F), and x denotes the number of functional termination groups. MXene materials exhibit unique properties, including strong light absorption across a broad spectral range, a high specific surface area, and excellent electrical and optical properties. These features make them excellent candidates for combination with MOFs. For instance, Wu et al successfully designed a Ti_3C_2-modulated MIL-125-NH_2 (*MTx*, where x denotes the amount of added Ti_3C_2) dual-heterojunction photocatalyst via a one-step hydrothermal method (113). They found that adding Ti_3C_2 into the precursor solution of NH_2-MIL-125(Ti) can significantly increase TiO_2 formation on the surface of NH_2-MIL-125(Ti). The optimum photocatalyst exhibited superior photocatalytic activity for tetracycline degradation. Accordingly, the MT5 sample exhibits 82.80% degradation of tetracycline in 60 minutes under visible-light irradiation, which was 11.43-fold higher than that of pure NH_2-MIL-125(Ti).

In recent years, applications of MOFs composed of perovskite materials, such as lanthanum ferrite ($LaFeO_3$) and cesium lead bromide ($CsPbBr_3$), have attracted significant attention. In a study conducted by Younes et al, the photocatalytic properties of MIL-125-NH_2, $LaFeO_3$, and $LaFeO_3$/MIL-125-NH_2 were investigated for the degradation of carbamazepine and caffeine (114). The results of the study indicated that the combination of $LaFeO_3$ and MIL-125-NH_2 ($LaFeO_3$/MIL-125-NH_2) demonstrated the highest photocatalytic performance. This finding suggests a synergistic effect between the two materials, where their combined properties enhanced the degradation of carbamazepine and caffeine. Asadi et al synthesized a novel $CsPbBr_3$/MOF-808 composite using a simple solvent-free mechanochemical grinding method (115). The photocatalytic degradation ability was assessed using three pharmaceutical compounds: ceftriaxone, vancomycin, and ceftazidime. The $CsPbBr_3$/MOF-808 photocatalyst composite showed degradation efficiencies of 97% and 87% for ceftriaxone and ceftazidime, respectively, whereas vancomycin displayed 12% degradation despite its strong adsorption capacity. The study concluded that the $CsPbBr_3$/MOF-808 sample showed a longer charge-carrier lifetime and greater e^-/h^+pair separation, thereby exhibiting higher photocatalytic activity.

In recent years, nanomaterials derived from MOFs have attracted significant attention for their stable performance and unique structures. These materials offer a promising solution to the problem of secondary pollution arising from the potential leaching of metal ions. Additionally, their porous carbon structure makes them highly effective photocatalysts for the treatment of pollutants. In a study by Cao et al, researchers successfully prepared novel nitrogen-doped carbon-supported cadmium sulfide (CdS/NC–T) composites via a facile in situ carbonization method (116). The researchers utilized cadmium MOFs as precursors for the synthesis of these composites. The CdS/NC–T composites were highly effective as photocatalysts for tetracycline degradation under visible irradiation (83% in 60 min). In their research, they found that the improved performance is attributed to the efficient production and transport of photogenerated carriers. The study found that the photocatalyst exhibited remarkable stability and reusability. After four rounds of recycling reactions, the catalyst retained over 80% of its initial catalytic capacity.

This finding demonstrates the photocatalyst's potential for practical applications, as it maintains its effectiveness across multiple cycles. The stability and reusability of the photocatalyst make it a promising candidate for sustainable and efficient photocatalytic degradation of tetracycline. Wang et al employed ZIF-8 as a sacrificial template and precursor to synthesize a nitrogen-doped ZnO carbon skeleton, denoted N-ZnO/C (117). Subsequently, hierarchical Bi_2MoO_6 nanosheets (BiM) were grown in situ on the surface of the N-ZnO/C material, forming a core-shell N-ZnO/C@BiM heterojunction. They successfully employed this photocatalyst for the removal of sulfamethoxazole

According to Table 3, several factors, including catalyst dose, initial pollutant concentration, and pH, are reported to affect performance in pharmaceutical photocatalytic degradation.

- **Catalyst dose:** Previous studies found that increasing the photocatalyst dosage positively affects the percentage of pharmaceutical degradation (118). This could be attributed to an increase in the number of active sites on the catalyst surface and the generation of more radicals at the surface, which substantially enhances photocatalytic activity (119). The solution becomes turbid beyond a specific limit of catalyst dosage, thereby hindering light penetration and reducing the degradation rate (120).
- **Initial pollutant concentration:** The initial concentration of organic pollutants plays an important role in tuning the photocatalytic activity (121). As the initial pharmaceutical concentration increases, the photocatalyst's active sites become saturated with target molecules, reducing light penetration. Consequently, degradation efficiency would decline.
- **Initial pH values:** pH is an important factor that affects the photocatalyst's adsorption capacity and degradation efficiency in the reaction system (55). Alterations in pH lead to changes in the catalyst's surface charge and the ionic forms of the pollutant molecules (122). It is worth noting that the photocatalyst surface carries a positive charge at pH values below the point of zero charge (pHzpc) and a negative charge at pH values above pHzpc (123). It can be concluded that similar charges on the target molecule and the catalyst result in low degradation efficiency.

Conclusion

The occurrence and ecological risk assessment of pharmaceutical residues have become critical topics due to their potential threats to the environment and human health. The application of advanced degradation techniques, such as photocatalytic processes, has attracted significant attention as an effective means of mitigating these risks. Photocatalysts, such as MOFs, have demonstrated high efficiency under suitable conditions, offering a promising pathway for sustainable pollutant management. MOFs have demonstrated remarkable potential for degrading pharmaceutical pollutants in water/wastewater due to their exceptional surface area, tunable porosity, and chemical versatility. MOF materials, in particular, have emerged as a promising solution for improving catalytic performance in water treatment processes. Recent studies have also focused on MOFs, known for their abundant pores and efficient light-harvesting abilities. However, the majority of pristine MOFs exhibit insufficient photocatalytic performance, primarily because of their low visible-light response and wide band gaps. To solve these problems, various composite system have been developed by integrated MOFs with metal oxides, metal sulfides, metal-free carbonaceous materials, noble metals, MXenes, and perovskites have been proposed to improve the photocatalytic performance of single MOF photocatalysts, thus opening new possibilities for pharmaceutical degradation.

Nevertheless, most studies using MOFs and MOF-based composite materials as photocatalysts for the degradation of pharmaceutical pollutants are still in their infancy and far from practical. Therefore, more research is needed to develop and optimize more efficient, cost-effective, and environmentally friendly MOF-based photocatalysts for environmental remediation. Also, to apply MOFs and MOF-based composite materials to real water/wastewater treatment, researchers should conduct additional experiments to determine the effects of various water/wastewater properties, such as ionic strength, nutrient content, and organic matter, on photocatalyst performance. To ensure that MOFs and MOF-based composite materials have a sustainable future, research should focus on developing photocatalysts that can be recycled with minimal energy and waste while maintaining chemical and physical stability across multiple photodegradation cycles.

In addition, it is essential to conduct an in-depth investigation into the kinetic and thermodynamic mechanisms that govern the synthesis of MOFs and MOF-based composite materials. Such studies are crucial for facilitating the development of more uniformly distributed active sites within these materials. By achieving greater control over their structural formation processes, it becomes possible to optimize their architecture and significantly enhance their photocatalytic efficiency.

In summary, this review provides a comprehensive overview of current research and development on MOFs and MOF-based composite materials, with a specific focus on their applications for the degradation of pharmaceutical contaminants. Additionally, it seeks to shed light on the key challenges ahead while exploring potential opportunities to advance this field.

Acknowledgements

The authors would like to thank Jiroft University of Medical Science for providing access to the literature needed for this research.

Authors' contributions

Conceptualization: Maryam Salimi.
Data curation: Maryam Salimi.
Formal Analysis: Maryam Salimi.
Investigation: Maryam Salimi.
Methodology: Maryam Salimi, Ali Esrafili, Ahmad Jonidi Jafari, Hamid Reza Sobhi.
Project administration: Maryam Salimi.
Resources: Maryam Salimi, Ali Esrafili, Ahmad Jonidi Jafari, Hamid Reza Sobhi.
Supervision: Maryam Salimi, Ali Esrafili, Ahmad jonidi Jafari, Hamid Reza Sobhi, Leili Esrafili.
Validation: Maryam Salimi, Ali Esrafili, Ahmad Jonidi Jafari, Hamid Reza Sobhi.
Visualization: Maryam Salimi.
Writing – original draft: Maryam Salimi.
Writing – review & editing: Maryam Salimi, Ali Esrafili, Ahmad Jonidi Jafari, Hamid Reza Sobhi.

Competing interests

The authors declare that there is no conflict of interest.

Ethical issues

In this manuscript, the authors have considered all ethical considerations related to data collection and affirm that this work is original. All data gathered during the study are accurately represented in the manuscript, and no data from this study has been or will be published separately elsewhere.

Funding

This research did not receive any specific funding from public, commercial, or non-profit organizations.

References

1. Salimi M, Behbahani M, Sobhi HR, Ghambarian M, Esrafili A. Trace measurement of lead and cadmium ions in wastewater samples using a novel dithizone immobilized metal–organic framework-based μ-dispersive solid-phase extraction. Appl Organomet Chem. 2020;34(8):e5715. doi: 10.1002/aoc.5715.
2. Sobhi HR, Behbahani M, Ghambarian M, Salimi M, Esrafili A. Extraction of carbonyl derivatives from ozonated wastewater samples using hollow fiber liquid phase microextraction followed by gas chromatography-electron capture detection. Microchem J. 2019;148:331-7. doi: 10.1016/j.microc.2019.05.020
3. Salimi M, Behbahani M, Sobhi HR, Ghambarian M, Esrafili A. Dispersive solid-phase extraction of selected nitrophenols from environmental water samples using a zirconium-based amino-tagged metal-organic framework nanosorbent. J Sep Sci. 2018;41(22):4159-66. doi: 10.1002/jssc.201800764
4. Bhat SA, Sher F, Hameed M, Bashir O, Kumar R, Vo DN, et al. Sustainable nanotechnology-based wastewater treatment strategies: achievements, challenges and future perspectives. Chemosphere. 2022;288(Pt 3):132606. doi: 10.1016/j.chemosphere.2021.132606
5. Nehra M, Dilbaghi N, Marrazza G, Kaushik A, Sonne C, Kim KH, et al. Emerging nanobiotechnology in agriculture for the management of pesticide residues. J Hazard Mater. 2021;401:123369. doi: 10.1016/j.jhazmat.2020.123369
6. Tang Z, Liu ZH, Wang H, Dang Z, Liu Y. A review of 17α-ethynylestradiol (EE2) in surface water across 32 countries: sources, concentrations, and potential estrogenic effects. J Environ Manage. 2021;292:112804. doi: 10.1016/j.jenvman.2021.112804
7. Kovalakova P, Cizmas L, McDonald TJ, Marsalek B, Feng M, Sharma VK. Occurrence and toxicity of antibiotics in the aquatic environment: a review. Chemosphere. 2020;251:126351. doi: 10.1016/j.chemosphere.2020.126351
8. Ding C, He J. Effect of antibiotics in the environment on microbial populations. Appl Microbiol Biotechnol. 2010;87(3):925-41. doi: 10.1007/s00253-010-2649-5
9. Yang Y, Ok YS, Kim KH, Kwon EE, Tsang YF. Occurrences and removal of pharmaceuticals and personal care products (PPCPs) in drinking water and water/sewage treatment plants: a review. Sci Total Environ. 2017;596-597:303-20. doi: 10.1016/j.scitotenv.2017.04.102
10. Majumder S, Chatterjee S, Basnet P, Mukherjee J. ZnO based nanomaterials for photocatalytic degradation of aqueous pharmaceutical waste solutions–a contemporary review. Environ Nanotechnol Monit Manag. 2020;14:100386. doi: 10.1016/j.enmm.2020.100386
11. Salimi M, Esrafili A, Gholami M, Jonidi Jafari A, Rezaei Kalantary R, Farzadkia M, et al. Contaminants of emerging concern: a review of new approach in AOP technologies. Environ Monit Assess. 2017;189(8):414. doi: 10.1007/s10661-017-6097-x
12. Esrafili A, Salimi M, Sobhi HR, Gholami M, Rezaei Kalantary R. Pt-based TiO2 photocatalytic systems: a systematic review. J Mol Liq. 2022;352:118685. doi: 10.1016/j.molliq.2022.118685
13. Salimi M, Behbahani M, Sobhi HR, Gholami M, Jonidi Jafari A, Rezaei Kalantary R, et al. A new nano-photocatalyst based on Pt and Bi Co-doped TiO2 for efficient visible-light photo degradation of amoxicillin. New J Chem. 2019;43(3):1562-8. doi: 10.1039/c8nj05020a
14. Salimi M, Esrafili A, Sobhi HR, Behbahani M, Gholami M, Farzadkia M, et al. Photocatalytic degradation of metronidazole using D-g-C3N4-Bi5O7I composites under visible light irradiation: degradation product, and mechanisms. ChemistrySelect. 2019;4(35):10288-95. doi: 10.1002/slct.201902369
15. Salimi M, Esrafili A, Jonidi Jafari A, Gholami M, Sobhi HR. Application of MIL-53 (Fe)/urchin-like g-C3N4 nanocomposite for efficient degradation of cefixime. Inorg Chem Commun. 2020;111:107565. doi: 10.1016/j.inoche.2019.107565
16. Felix Sahayaraj A, Joy Prabu H, Maniraj J, Kannan M, Bharathi M, Diwahar P, et al. Metal–organic frameworks (MOFs): the next generation of materials for catalysis, gas storage, and separation. J Inorg Organomet Polym Mater. 2023;33(7):1757-81. doi: 10.1007/s10904-023-02657-1
17. Li Y, Fang Y, Cao Z, Li N, Chen D, Xu Q, et al. Construction of g-C3N4/PDI@MOF heterojunctions for the highly

efficient visible light-driven degradation of pharmaceutical and phenolic micropollutants. Appl Catal B Environ. 2019;250:150-62. doi: 10.1016/j.apcatb.2019.03.024
18. Xu Q, Zhang L, Cheng B, Fan J, Yu J. S-scheme heterojunction photocatalyst. Chem. 2020;6(7):1543-59. doi: 10.1016/j.chempr.2020.06.010
19. Férey G, Serre C, Mellot-Draznieks C, Millange F, Surblé S, Dutour J, et al. A hybrid solid with giant pores prepared by a combination of targeted chemistry, simulation, and powder diffraction. Angew Chem Int Ed Engl. 2004;43(46):6296-301. doi: 10.1002/anie.200460592
20. Huang XC, Lin YY, Zhang JP, Chen XM. Ligand-directed strategy for zeolite-type metal-organic frameworks: zinc(II) imidazolates with unusual zeolitic topologies. Angew Chem Int Ed Engl. 2006;45(10):1557-9. doi: 10.1002/anie.200503778
21. Cavka JH, Jakobsen S, Olsbye U, Guillou N, Lamberti C, Bordiga S, et al. A new zirconium inorganic building brick forming metal organic frameworks with exceptional stability. J Am Chem Soc. 2008;130(42):13850-1. doi: 10.1021/ja8057953
22. Fan W, Wang KY, Welton C, Feng L, Wang X, Liu X, et al. Aluminum metal–organic frameworks: from structures to applications. Coord Chem Rev. 2023;489:215175. doi: 10.1016/j.ccr.2023.215175
23. Luo S, Zeng Z, Zeng G, Liu Z, Xiao R, Chen M, et al. Metal organic frameworks as robust host of palladium nanoparticles in heterogeneous catalysis: synthesis, application, and prospect. ACS Appl Mater Interfaces. 2019;11(36):32579-98. doi: 10.1021/acsami.9b11990
24. Janiak C, Vieth JK. MOFs, MILs and more: concepts, properties and applications for porous coordination networks (PCNs). New J Chem. 2010;34(11):2366-88. doi: 10.1039/c0nj00275e
25. Zhao T, Nie S, Luo M, Xiao P, Zou M, Chen Y. Research progress in structural regulation and applications of HKUST-1 and HKUST-1 based materials. J Alloys Compd. 2024;974:172897. doi: 10.1016/j.jallcom.2023.172897
26. Luo Z, Yin D, Tao L, Ren J. Fabrication of a heterojunction by coupling a metal-organic framework and N-doped carbon for the photocatalytic removal of antibiotic drugs with high efficiency. Langmuir. 2022;38(42):12968-80. doi: 10.1021/acs.langmuir.2c02256
27. El-Fawal EM, Younis SA, Zaki T. Designing AgFeO2-graphene/Cu2(BTC)3 MOF heterojunction photocatalysts for enhanced treatment of pharmaceutical wastewater under sunlight. J Photochem Photobiol A Chem. 2020;401:112746. doi: 10.1016/j.jphotochem.2020.112746
28. Cao J, Yang ZH, Xiong WP, Zhou YY, Peng YR, Li X, et al. One-step synthesis of Co-doped UiO-66 nanoparticle with enhanced removal efficiency of tetracycline: simultaneous adsorption and photocatalysis. Chem Eng J. 2018;353:126-37. doi: 10.1016/j.cej.2018.07.060
29. Jing S, Wang H, Wang A, Cheng R, Liang H, Chen F, et al. Surface plasmon resonance bismuth-modified NH2-UiO-66 with enhanced photocatalytic tetracycline degradation performance. J Colloid Interface Sci. 2024;655:120-32. doi: 10.1016/j.jcis.2023.10.149
30. Ji Q, Yan X, Xu J, Wang C, Wang L. Fabrication of hollow type-II and Z-scheme In2O3/TiO2/Cu2O photocatalyst based on In-MIL-68 for efficient catalytic degradation of tetracycline. Sep Purif Technol. 2021;265:118487. doi: 10.1016/j.seppur.2021.118487
31. Mheidli N, Malli A, Mansour F, Al-Hindi M. Occurrence and risk assessment of pharmaceuticals in surface waters of the Middle East and North Africa: a review. Sci Total Environ. 2022;851(Pt 2):158302. doi: 10.1016/j.scitotenv.2022.158302
32. Liu JL, Wong MH. Pharmaceuticals and personal care products (PPCPs): a review on environmental contamination in China. Environ Int. 2013;59:208-24. doi: 10.1016/j.envint.2013.06.012
33. Singh V, Suthar S. Occurrence, seasonal variations, and ecological risk of pharmaceuticals and personal care products in River Ganges at two holy cities of India. Chemosphere. 2021;268:129331. doi: 10.1016/j.chemosphere.2020.129331
34. Ebele AJ, Oluseyi T, Drage DS, Harrad S, Abdallah MA. Occurrence, seasonal variation and human exposure to pharmaceuticals and personal care products in surface water, groundwater and drinking water in Lagos state, Nigeria. Emerg Contam. 2020;6:124-32. doi: 10.1016/j.emcon.2020.02.004
35. Kumar R, Sarmah AK, Padhye LP. Fate of pharmaceuticals and personal care products in a wastewater treatment plant with parallel secondary wastewater treatment train. J Environ Manage. 2019;233:649-59. doi: 10.1016/j.jenvman.2018.12.062
36. Huang YH, Liu Y, Du PP, Zeng LJ, Mo CH, Li YW, et al. Occurrence and distribution of antibiotics and antibiotic resistant genes in water and sediments of urban rivers with black-odor water in Guangzhou, South China. Sci Total Environ. 2019;670:170-80. doi: 10.1016/j.scitotenv.2019.03.168
37. Nantaba F, Wasswa J, Kylin H, Palm WU, Bouwman H, Kümmerer K. Occurrence, distribution, and ecotoxicological risk assessment of selected pharmaceutical compounds in water from Lake Victoria, Uganda. Chemosphere. 2020;239:124642. doi: 10.1016/j.chemosphere.2019.124642
38. Bai Y, Meng W, Xu J, Zhang Y, Guo C. Occurrence, distribution and bioaccumulation of antibiotics in the Liao river basin in China. Environ Sci Process Impacts. 2014;16(3):586-93. doi: 10.1039/c3em00567d
39. Li D, Shao H, Huo Z, Xie N, Gu J, Xu G. Typical antibiotics in the receiving rivers of direct-discharge sources of sewage across Shanghai: occurrence and source analysis. RSC Adv. 2021;11(35):21579-87. doi: 10.1039/d1ra02510d
40. Ranjan N, Singh PK, Maurya NS. Pharmaceuticals in water as emerging pollutants for river health: a critical review under Indian conditions. Ecotoxicol Environ Saf. 2022;247:114220. doi: 10.1016/j.ecoenv.2022.114220
41. Hossain A, Nakamichi S, Habibullah-Al-Mamun M, Tani K, Masunaga S, Matsuda H. Occurrence and ecological risk of pharmaceuticals in river surface water of Bangladesh. Environ Res. 2018;165:258-66. doi: 10.1016/j.envres.2018.04.030
42. Mohd Nasir FA, Praveena SM, Aris AZ. Public awareness level and occurrence of pharmaceutical residues in drinking water with potential health risk: a study from Kajang (Malaysia). Ecotoxicol Environ Saf. 2019;185:109681. doi: 10.1016/j.ecoenv.2019.109681
43. Lolić A, Paíga P, Santos LH, Ramos S, Correia M, Delerue-Matos C. Assessment of non-steroidal anti-inflammatory and analgesic pharmaceuticals in seawaters of North of Portugal: occurrence and environmental risk. Sci Total Environ. 2015;508:240-50. doi: 10.1016/j.

scitotenv.2014.11.097
44. Linghu K, Wu Q, Zhang J, Wang Z, Zeng J, Gao S. Occurrence, distribution and ecological risk assessment of antibiotics in Nanming river: contribution from wastewater treatment plant and implications of urban river syndrome. Process Saf Environ Prot. 2023;169:428-36. doi: 10.1016/j.psep.2022.11.025
45. Senasu T, Chankhanittha T, Hemavibool K, Nanan S. Solvothermal synthesis of BiOBr photocatalyst with an assistant of PVP for visible-light-driven photocatalytic degradation of fluoroquinolone antibiotics. Catal Today. 2022;384-386:209-27. doi: 10.1016/j.cattod.2021.04.008
46. Huang J, Wang B, Hao Z, Zhou Z, Qu Y. Boosting charge separation and broadening NIR light response over defected WO3 quantum dots coupled g-C3N4 nanosheets for photocatalytic degrading antibiotics. Chem Eng J. 2021;416:129109. doi: 10.1016/j.cej.2021.129109
47. Ni S, Fu Z, Li L, Ma M, Liu Y. Step-scheme heterojunction g-C3N4/TiO2 for efficient photocatalytic degradation of tetracycline hydrochloride under UV light. Colloids Surf A Physicochem Eng Asp. 2022;649:129475. doi: 10.1016/j.colsurfa.2022.129475
48. Hou D, Zhu Q, Wang J, Deng M, Qiao XQ, Sun B, et al. Direct Z-scheme system of UiO-66 cubes wrapped with Zn(0.5)Cd(0.5)S nanoparticles for photocatalytic hydrogen generation synchronized with organic pollutant degradation. J Colloid Interface Sci. 2024;665:68-79. doi: 10.1016/j.jcis.2024.03.111
49. Chen L, Peng J, Wang F, Liu D, Ma W, Zhang J, et al. ZnO nanorods/Fe3O4-graphene oxide/metal-organic framework nanocomposite: recyclable and robust photocatalyst for degradation of pharmaceutical pollutants. Environ Sci Pollut Res Int. 2021;28(17):21799-811. doi: 10.1007/s11356-020-12253-2
50. Lin Z, Wu Y, Jin X, Liang D, Jin Y, Huang S, et al. Facile synthesis of direct Z-scheme UiO-66-NH2/PhC2Cu heterojunction with ultrahigh redox potential for enhanced photocatalytic Cr(VI) reduction and NOR degradation. J Hazard Mater. 2023;443(Pt A):130195. doi: 10.1016/j.jhazmat.2022.130195
51. Su Q, Li J, Wang B, Li Y, Hou LA. Direct Z-scheme Bi2MoO6/UiO-66-NH2 heterojunctions for enhanced photocatalytic degradation of ofloxacin and ciprofloxacin under visible light. Appl Catal B Environ. 2022;318:121820. doi: 10.1016/j.apcatb.2022.121820
52. Gao W, Li Y, Xie W, Huang J, Li L, Qiu Z. Photocatalytic degradation of oxytetracycline using zeolite imidazole framework-8 (ZIF-8) as an effective catalyst. Nano. 2022;17(6):2250042. doi: 10.1142/s1793292022500424
53. Wang YL, Zhang S, Zhao YF, Bedia J, Rodriguez JJ, Belver C. UiO-66-based metal organic frameworks for the photodegradation of acetaminophen under simulated solar irradiation. J Environ Chem Eng. 2021;9(5):106087. doi: 10.1016/j.jece.2021.106087
54. Sheikhsamany R, Nezamzadeh-Ejhieh A, Ensandoost R, Kakavandi B. BaTi0.85Zr0. 15O3/MOF-5 nanocomposite: synthesis, characterization and photocatalytic activity toward tetracycline. J Mol Liq. 2024;403:124850. doi: 10.1016/j.molliq.2024.124850
55. Wu M, Huang M, Zhang B, Li Y, Liu S, Wang H, et al. Construction of 3D porous BiOBr/MIL-101(Cr) Z-scheme heterostructure for boosted photocatalytic degradation of tetracycline hydrochloride. Sep Purif Technol. 2023;307:122744. doi: 10.1016/j.seppur.2022.122744
56. Xie J, Tang Y, Chen F, Hao CC. A visible light responsive Bi2S3/MIL-53(Fe) heterojunction with enhanced photocatalytic activity for degradation of tetracycline. J Phys Chem Solids. 2023;181:111551. doi: 10.1016/j.jpcs.2023.111551
57. Chen F, Bian K, Li H, Tang Y, Hao C, Shi W. A novel CeO2/MIL101(Fe) heterojunction for enhanced photocatalytic degradation of tetracycline under visible-light irradiation. J Chem Technol Biotechnol. 2022;97(7):1884-92. doi: 10.1002/jctb.7061
58. Sheikhsamany R, Faghihian H, Fazaeli R. Synthesis of novel HKUST-1-based SnO2 porous nanocomposite with the photocatalytic capability for degradation of metronidazole. Mater Sci Semicond Process. 2022;138:106310. doi: 10.1016/j.mssp.2021.106310
59. Zhou Y, Yao T, Tan Y, Chen Y, Chen Z, Zhang J. Preparation of a novel composite material aluminum-based MOF(DUT-5)/Bi2MoO6 for degradation of tetracycline. Catal Lett. 2023;153(6):1743-55. doi: 10.1007/s10562-022-04091-3
60. Wang F, He T, Gao Y, Li Y, Cui S, Huang H, et al. Z-scheme heterojunction Bi2MoO6/NH2-UiO-66(Zr/Ce) for efficient photocatalytic degradation of oxytetracycline: pathways and mechanism. Sep Purif Technol. 2023;325:124596. doi: 10.1016/j.seppur.2023.124596
61. Dai X, Feng S, Wu W, Zhou Y, Ye Z, Wang Y, et al. Photocatalytic degradation of tetracycline by Z-scheme Bi2WO6/ZIF-8. J Inorg Organomet Polym Mater. 2022;32(7):2371-83. doi: 10.1007/s10904-022-02273-5
62. Wang Y, Lin L, Dong Y, Liu X. Facile synthesis of MOF-808/AgI Z-scheme heterojunction with improved photocatalytic performance for the degradation of tetracycline hydrochloride under simulated sunlight. New J Chem. 2022;46(34):16584–92. doi: 10.1039/d2nj03301a
63. Tang J, Gao G, Luo W, Dai Q, Wang Y, Elzilal HA, et al. Z-scheme metal organic framework@graphene oxide composite photocatalysts with enhanced photocatalytic degradation of tetracycline. Adv Compos Hybrid Mater. 2023;6(6):190. doi: 10.1007/s42114-023-00771-9
64. Su Q, Li J, Yuan H, Wang B, Wang Y, Li Y, et al. Visible-light-driven photocatalytic degradation of ofloxacin by g-C3N4/NH2-MIL-88B(Fe) heterostructure: mechanisms, DFT calculation, degradation pathway and toxicity evolution. Chem Eng J. 2022;427:131594. doi: 10.1016/j.cej.2021.131594
65. He H, Liang B, Lin S, Chen Y, Zhang X, Liang SX. Photodegradation of oxytetracycline hydrochloride by Z-scheme g-C3N4@ MIL-101(Fe) heterojunction: experimental optimization, mechanism evaluation and practical application. J Environ Chem Eng. 2024;12(2):112018. doi: 10.1016/j.jece.2024.112018
66. Harrabi M, Della Giustina SV, Aloulou F, Rodriguez-Mozaz S, Barceló D, Elleuch B. Analysis of multiclass antibiotic residues in urban wastewater in Tunisia. Environ Nanotechnol Monit Manag. 2018;10:163-70. doi: 10.1016/j.enmm.2018.05.006
67. Younes HA, Mahmoud HM, Abdelrahman MM, Nassar HF. Seasonal occurrence, removal efficiency and associated ecological risk assessment of three antibiotics in a municipal wastewater treatment plant in Egypt. Environ Nanotechnol Monit Manag. 2019;12:100239. doi: 10.1016/j.enmm.2019.100239

68. Al-Maadheed S, Goktepe I, Latiff AB, Shomar B. Antibiotics in hospital effluent and domestic wastewater treatment plants in Doha, Qatar. J Water Process Eng. 2019;28:60-8. doi: 10.1016/j.jwpe.2019.01.005
69. Ngigi AN, Magu MM, Muendo BM. Occurrence of antibiotics residues in hospital wastewater, wastewater treatment plant, and in surface water in Nairobi county, Kenya. Environ Monit Assess. 2019;192(1):18. doi: 10.1007/s10661-019-7952-8
70. Zhi S, Shen S, Zhou J, Ding G, Zhang K. Systematic analysis of occurrence, density and ecological risks of 45 veterinary antibiotics: focused on family livestock farms in Erhai Lake basin, Yunnan, China. Environ Pollut. 2020;267:115539. doi: 10.1016/j.envpol.2020.115539
71. Paíga P, Santos L, Ramos S, Jorge S, Silva JG, Delerue-Matos C. Presence of pharmaceuticals in the Lis river (Portugal): sources, fate and seasonal variation. Sci Total Environ. 2016;573:164-77. doi: 10.1016/j.scitotenv.2016.08.089
72. Lei K, Zhu Y, Chen W, Pan HY, Cao YX, Zhang X, et al. Spatial and seasonal variations of antibiotics in river waters in the Haihe river catchment in China and ecotoxicological risk assessment. Environ Int. 2019;130:104919. doi: 10.1016/j.envint.2019.104919
73. Wu Y, Li Y, Li H, Guo H, Yang Q, Li X. Tunning heterostructures interface of Cu2O@HKUST-1 for enhanced photocatalytic degradation of tetracycline hydrochloride. Sep Purif Technol. 2022;303:122106. doi: 10.1016/j.seppur.2022.122106
74. Tang L, Lv ZQ, Xue YC, Xu L, Qiu WH, Zheng CM, et al. MIL-53(Fe) incorporated in the lamellar BiOBr: promoting the visible-light catalytic capability on the degradation of rhodamine B and carbamazepine. Chem Eng J. 2019;374:975-82. doi: 10.1016/j.cej.2019.06.019
75. Chen FZ, Li YJ, Zhou M, Gong XX, Gao Y, Cheng G, et al. Smart multifunctional direct Z-scheme In2S3@PCN-224 heterojunction for simultaneous detection and photodegradation towards antibiotic pollutants. Appl Catal B Environ. 2023;328:122517. doi: 10.1016/j.apcatb.2023.122517
76. Zhu L, Chen Y, Liu X, Si Y, Tang Y, Wang X. MoS2-modified MIL-53(Fe) for synergistic adsorption-photocatalytic degradation of tetracycline. Environ Sci Pollut Res Int. 2023;30(9):23086-95. doi: 10.1007/s11356-022-23859-z
77. He L, Dong Y, Zheng Y, Jia Q, Shan S, Zhang Y. A novel magnetic MIL-101(Fe)/TiO2 composite for photo degradation of tetracycline under solar light. J Hazard Mater. 2019;361:85-94. doi: 10.1016/j.jhazmat.2018.08.079
78. He X, Fang H, Gosztola DJ, Jiang Z, Jena P, Wang WN. Mechanistic insight into photocatalytic pathways of MIL-100(Fe)/TiO2 composites. ACS Appl Mater Interfaces. 2019;11(13):12516-24. doi: 10.1021/acsami.9b00223
79. He L, Zhang Y, Zheng Y, Jia Q, Shan S, Dong Y. Degradation of tetracycline by a novel MIL-101(Fe)/TiO2 composite with persulfate. J Porous Mater. 2019;26(6):1839-50. doi: 10.1007/s10934-019-00778-y
80. Wu J, Fang X, Zhu Y, Ma N, Dai W. Well-designed TiO2@UiO-66-NH2 nanocomposite with superior photocatalytic activity for tetracycline under restricted space. Energy Fuels. 2020;34(10):12911-7. doi: 10.1021/acs.energyfuels.0c02485
81. Nazari S, Asgari E, Sheikhmohammadi A, Mokhtari SA, Alamgholiloo H. Visible-light-driven photocatalytic activity of WO3/ZIF-67 S-scheme heterojunction for upgrading degradation of oxytetracycline. J Environ Chem Eng. 2023;110393. doi: 10.1016/j.jece.2023.110393
82. Kaur M, Mehta SK, Devi P, Kansal SK. Bi2WO6/NH2-MIL-88B(Fe) heterostructure: an efficient sunlight driven photocatalyst for the degradation of antibiotic tetracycline in aqueous medium. Adv Powder Technol. 2021;32(12):4788-804. doi: 10.1016/j.apt.2021.10.025
83. Dai D, Qiu J, Li M, Xu J, Zhang L, Yao J. Construction of two-dimensional BiOI on carboxyl-rich MIL-121 for visible-light photocatalytic degradation of tetracycline. J Alloys Compd. 2021;872:159711. doi: 10.1016/j.jallcom.2021.159711
84. Tang J, Zhang T, Zhang Q, Duan Z, Li C, Hou D, et al. In-situ growth UiO-66 on Bi2O3 to fabrication pp heterojunction with enhanced visible-light degradation of tetracycline. J Solid State Chem. 2021;302:122353. doi: 10.1016/j.jssc.2021.122353
85. Zhang H, Meng Q, Li H, Wu G, Li K, Xu J, et al. BiOI nanoparticle/PCN-222 heterojunctions as self-decontaminating photocatalysts with efficient tetracycline visible-light degradation. CrystEngComm. 2022;24(43):7611-9. doi: 10.1039/d2ce01109c
86. Wang Y, Chen T, Xu H, Yu J, Zhang T. A flower-like heterojunction for highly photocatalytic treating oxytetracycline based on chrome-based metal-organic frameworks decorated BiOCl nanosheet. Colloids Surf A Physicochem Eng Asp. 2024;685:133259. doi: 10.1016/j.colsurfa.2024.133259
87. He Y, Wang D, Li X, Fu Q, Yin L, Yang Q, et al. Photocatalytic degradation of tetracycline by metal-organic frameworks modified with Bi2WO6 nanosheet under direct sunlight. Chemosphere. 2021;284:131386. doi: 10.1016/j.chemosphere.2021.131386
88. Wu C, Shen Q, Zheng S, Zhang X, Sheng J, Yang H. Fabrication of Bi2Sn2O7@MIL-100(Fe) composite photocatalyst with enhanced superoxide-radical-dominated photocatalytic activity for ciprofloxacin degradation. J Mol Struct. 2022;1258:132657. doi: 10.1016/j.molstruc.2022.132657
89. Zhang J, Qian C, Chen W, Huang H. 1D CuBi2O4@2D UiO-66-NH2 core-shell nanostructures for photodegradation of tetracycline hydrochloride. ACS Appl Nano Mater. 2023;6(21):20062-73. doi: 10.1021/acsanm.3c03862
90. Jin Y, Mi X, Qian J, Ma N, Dai W. CdS nanoparticles supported on a dual metal–organic framework as a catalyst for the photodegradation of tetracycline. ACS Appl Nano Mater. 2024 ;7(3):3154-67. doi: 10.1021/acsanm.3c05511
91. He Y, Dong W, Li X, Wang D, Yang Q, Deng P, et al. Modified MIL-100(Fe) for enhanced photocatalytic degradation of tetracycline under visible-light irradiation. J Colloid Interface Sci. 2020;574:364-76. doi: 10.1016/j.jcis.2020.04.075
92. Jin P, Wang L, Ma X, Lian R, Huang J, She H, et al. Construction of hierarchical ZnIn2S4@PCN-224 heterojunction for boosting photocatalytic performance in hydrogen production and degradation of tetracycline hydrochloride. Appl Catal B Environ. 2021;284:119762. doi: 10.1016/j.apcatb.2020.119762
93. Zhang X, Zhang N, Gan C, Liu Y, Chen L, Zhang C, et al. Synthesis of In2S3/UiO-66 hybrid with enhanced photocatalytic activity towards methyl orange and tetracycline hydrochloride degradation under visible-light irradiation. Mater Sci Semicond Process. 2019;91:212-21. doi: 10.1016/j.mssp.2018.11.014
94. Chaturvedi G, Kaur A, Kansal SK. CdS-decorated

MIL-53(Fe) microrods with enhanced visible light photocatalytic performance for the degradation of ketorolac tromethamine and mechanism insight. J Phys Chem C. 2019;123(27):16857-67. doi: 10.1021/acs.jpcc.9b04312
95. Zhang X, Liu Z, Shao B, Wu T, Pan Y, Luo S, et al. Construction of ZnIn2S4/MOF-525 heterojunction system to enhance photocatalytic degradation of tetracycline. Environ Sci Pollut Res Int. 2023;30(25):67647-61. doi: 10.1007/s11356-023-27282-w
96. Ren S, Dong J, Duan X, Cao T, Yu H, Lu Y, et al. A novel (Zr/Ce)UiO-66 (NH2)@g-C3N4 Z-scheme heterojunction for boosted tetracycline photodegradation via effective electron transfer. Chem Eng J. 2023;460:141884. doi: 10.1016/j.cej.2023.141884
97. Bilgin Simsek E. Carbon-based metal-free catalysts for photocatalytic reactions. In: Carbon-Based Metal Free Catalysts. Elsevier; 2022. p. 151-94. doi: 10.1016/b978-0-323-88515-7.00009-2
98. Wu Z, Chen Z, Chen J, Ning X, Chen P, Jiang H, et al. Enhanced adsorption and synergistic photocatalytic degradation of tetracycline by MOF-801/GO composites via solvothermal synthesis. Environ Sci Nano. 2022;9(12):4609-18. doi: 10.1039/d2en00809b
99. Mi X, Li X. Construction of a stable porous composite with tunable graphene oxide in Ce-based-MOFs for enhanced solar-photocatalytic degradation of sulfamethoxazole in water. Sep Purif Technol. 2022;301:122006. doi: 10.1016/j.seppur.2022.122006
100. Zhang Q, Xu J, Ma X, Xu J, Yun Z, Zuo Q, et al. A novel Fe-based bi-MOFs material for photocatalytic degradation of tetracycline: performance, mechanism and toxicity assessment. J Water Process Eng. 2021;44:102364. doi: 10.1016/j.jwpe.2021.102364
101. Zheng X, Li Y, Yang J, Cui S. Z-scheme heterojunction Ag/NH2-MIL-125(Ti)/CdS with enhanced photocatalytic activity for ketoprofen degradation: mechanism and intermediates. Chem Eng J. 2021;422:130105. doi: 10.1016/j.cej.2021.130105
102. Li H, Xia Q, Liu X, Hu L, Zhong J, Lu F, et al. Construction of functional direct Z-scheme PCN-224@MoS2 heterojunction with high photocatalytic performance by simple solvothermal method. J Environ Chem Eng. 2024;112447. doi: 10.1016/j.jece.2024.112447
103. Salimi M, Esrafili A, Jonidi Jafari A, Gholami M, Sobhi HR, Nourbakhsh M, et al. Photocatalytic degradation of cefixime with MIL-125(Ti)-mixed linker decorated by g-C3N4 under solar driven light irradiation. Colloids Surf A Physicochem Eng Asp. 2019;582:123874. doi: 10.1016/j.colsurfa.2019.123874
104. Cao W, Yuan Y, Yang C, Wu S, Cheng J. In-situ fabrication of g-C3N4/MIL-68(In)-NH2 heterojunction composites with enhanced visible-light photocatalytic activity for degradation of ibuprofen. Chem Eng J. 2020;391:123608. doi: 10.1016/j.cej.2019.123608
105. Miao S, Zhang H, Cui S, Yang J. Improved photocatalytic degradation of ketoprofen by Pt/MIL-125(Ti)/Ag with synergetic effect of Pt-MOF and MOF-Ag double interfaces: mechanism and degradation pathway. Chemosphere. 2020;257:127123. doi: 10.1016/j.chemosphere.2020.127123
106. Zhang F, Xiao X, Xiao Y, Cheng X. Construction of novel 0D/2D AgI/CAU-17 heterojunction with excellent photocatalytic performance by in situ deposition-precipitation. J Environ Chem Eng. 2023;11(2):109641. doi: 10.1016/j.jece.2023.109641
107. Jiang D, Zhou Y, Wang P, Huang C, Zhu J, Liu Z. Acid-modulated porous AgI/D-MIL-53(Fe) composites for the removal of antibiotic contaminant. J Mater Sci. 2021;56(28):15782-97. doi: 10.1007/s10853-021-06321-2
108. Muelas-Ramos V, Belver C, Rodriguez JJ, Bedia J. Synthesis of noble metal-decorated NH2-MIL-125 titanium MOF for the photocatalytic degradation of acetaminophen under solar irradiation. Sep Purif Technol. 2021;272:118896. doi: 10.1016/j.seppur.2021.118896
109. Yang T, Ma T, Yang L, Dai W, Zhang S, Luo S. A self-supporting UiO-66 photocatalyst with Pd nanoparticles for efficient degradation of tetracycline. Appl Surf Sci. 2021;544:148928. doi: 10.1016/j.apsusc.2021.148928
110. Liu X, Zhao X, Meng H, Jin J. Dual MOFs composites: MIL-53 coated with amorphous UiO-66 for enhanced photocatalytic oxidation of tetracycline and methylene blue. Nano Res. 2023;16(5):6160–6. doi: 10.1007/s12274-022-5200-y
111. Zhao Y, Zhang Y, Cao X, Li J, Hou X. Synthesis of MOF on MOF photocatalysts using PCN-134 as seed through epitaxial growth strategy towards nizatidine degradation. Chem Eng J. 2023;465:143000. doi: 10.1016/j.cej.2023.143000
112. Gao T, Zhang H, Zhao X, Xiao S, Zhang Z, Yu S. Efficient removal of tetracycline from MOF-on-MOF heterojunctions driven by visible light: evaluation of photocatalytic mechanisms and degradation pathway. Appl Surf Sci. 2024;651:159227. doi: 10.1016/j.apsusc.2023.159227
113. Wu Y, Li X, Yang Q, Wang D, Yao F, Cao J, et al. Mxene-modulated dual-heterojunction generation on a metal-organic framework (MOF) via surface constitution reconstruction for enhanced photocatalytic activity. Chem Eng J. 2020;390:124519. doi: 10.1016/j.cej.2020.124519
114. Younes HA, Taha M, Khaled R, Mahmoud HM, Abdelhameed RM. Perovskite/metal-organic framework photocatalyst: a novel nominee for eco-friendly uptake of pharmaceuticals from wastewater. J Alloys Compd. 2023;930:167322. doi: 10.1016/j.jallcom.2022.167322
115. Asadi A, Khosroshahi N, Safarifard V. Engineering water-stable metal halide perovskite/MOF-808 heterojunction through mechanochemical method: S-scheme photocatalytic system for multifunctional applications. Mater Sci Semicond Process. 2023;165:107707. doi: 10.1016/j.mssp.2023.107707
116. Cao HL, Cai FY, Yu K, Zhang YQ, Lu¨ J, Cao R. Photocatalytic degradation of tetracycline antibiotics over CdS/nitrogen-doped–carbon composites derived from in situ carbonization of metal-organic frameworks. ACS Sustain Chem Eng. 2019;7(12):10847-54. doi: 10.1021/acssuschemeng.9b01685
117. Wang A, Ni J, Wang W, Wang X, Liu D, Zhu Q. MOF-derived N-doped ZnO carbon skeleton@hierarchical Bi2MoO6 S-scheme heterojunction for photodegradation of SMX: mechanism, pathways and DFT calculation. J Hazard Mater. 2022;426:128106. doi: 10.1016/j.jhazmat.2021.128106
118. Sheikhsamany R, Faghihian H, Fazaeli R. One-pot synthesis of BaTi0.85Zr0. 15O3/MOF-199 (HKUST-1) as a highly efficient photocatalytic nanocomposite for tetracycline degradation under UV irradiation. Inorg Chem Commun. 2021;134:109048. doi: 10.1016/j.inoche.2021.109048
119. Fawzy A, Mahanna H, Mossad M. Effective photocatalytic degradation of amoxicillin using MIL-53(Al)/ZnO

composite. Environ Sci Pollut Res Int. 2022;29(45):68532-46. doi: 10.1007/s11356-022-20527-0

120. Guo H, Song J, Zhang Q, Qiu L, Kang X, Wang L. Construction of Z-scheme NH2-UiO-66/Bi2O2CO3 heterojunction with enhanced photocatalytic degradation of TC under visible light. Opt Mater (Amst). 2023;139:113729. doi: 10.1016/j.optmat.2023.113729
121. Gao Y, Yang W, Wang F, Li Y, Cui S, Liao X, et al. Photocatalytic degradation of oxytetracycline by UiO-66 doped three-dimensional flower-like MoS2 heterojunction: DFT, degradation pathways, mechanism. J Taiwan Inst Chem Eng. 2023;152:105160. doi: 10.1016/j.jtice.2023.105160
122. Ma Y, Qian X, Arif M, Xia J, Fan H, Luo J, et al. Z-scheme Bi4O5Br2/MIL-88B(Fe) heterojunction for boosting visible light catalytic oxidation of tetracycline hydrochloride. Appl Surf Sci. 2023;611(Pt A):155667. doi: 10.1016/j.apsusc.2022.155667
123. Wang Q, Qian X, Xu H, He G, Chen H. Enriched surface oxygen vacancies of Bi2WO6/NH2-MIL-68(In) Z-scheme heterojunction with boosted visible-light photocatalytic degradation for levofloxacin: performance, degradation pathway and mechanism insight. Sep Purif Technol. 2023;306(Pt A):122577. doi: 10.1016/j.seppur.2022.122577